

POWER ADHESIVE BISONITE

UNIVERSAL POLYURETHANE ADHESIVE FOR THE MOST DIFFICULT JOINTS.



PRODUCT DESCRIPTION

Universal dual-component polyurethane adhesive, for the most difficult joints.

FIELD OF APPLICATION

Bonds many materials where other adhesives fail, such as metal, iron, stainless steel, aluminium, zinc, concrete, stone, marble, ceramic wall and floor tiles, wood, glass, rubber and many synthetics. Especially suitable for adhesive bonding of synthetic materials with other materials. Not suitable for bonding Polyethylene (PE), Polypropylene (PP), PTFE and silicone.

PROPERTIES

- For the toughest connections
- (Sea)water resistant
- Cold and heat resistant between -30°C and +100°C
- Strength 180 kg/cm²

PREPARATION

Working conditions: Do not use at temperatures below +5°C. The wood moisture content should not exceed 18%.

Personal safety: It is recommended that rubber or plastic gloves are worn.

Surface requirements: The surface must be clean, dry, free of dust and grease.

Preliminary surface treatment: If necessary, degrease with Bison Degreaser or acetone. With smooth surfaces light sanding provides a stronger bond.

Tools: Enclosed spatula

APPLICATION

Dilute: May not be diluted.

Mixture ratio: 1 part hardener to 4 parts resin

Coverage: 0.15 m² - 0.30 m²/65 ml, depending on the substrate and whether

the materials to be bonded are coated completely or dot-wise.

Directions for use:

The adhesive consists of two components: Resin and hardener. Press gently out both tubes two equally long lines of product. This way you get exactly the correct mixture ratio of resin and hardener (4 vol. parts resin to 1 vol. part hardener). Mix both components thoroughly with the supplied spatula into a mass of homogeneous color. The adhesive mix, depending on the temperature and the nature of the material, remains workable for about 15 minutes. Apply the adhesive mixture on one side of the substrate or the materials to be bonded, join the parts and keep them firmly in place (preferably clamp or support). Remove excess adhesive immediately with a cloth.

Potlife: 15 minutes

Stains/residue: Remove adhesive residue immediately with acetone. Dry adhesive residue can only be removed mechanically.

Advice: Some types of synthetics can not be joined such as polyethylene and polypropylene. This can be tested by holding a glowing copper wire against the synthetics. Does it smell of wax? Then you can not bond it.

Use a piece of adhesive tape in order to keep the parts in place while the adhesive is curing.

CURE TIMES

Handling time: approx. 1 hour

Full bond strength: Full bond strength after approx. 48 hours

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Water resistance: Very good

Temperature resistance: -30°C to +100°C

UV resistance: Very good

Chemicals resistance: Very good

TECHNICAL SPECIFICATIONS

Chemical base: Resin: polyol, hardener: isocyanate

Colour: Beige (mixture)

Viscosity: Thixotropic

Solid contents: approx. 100 %

Density: approx. 1.4 g/cm³

Final bond strength: approx. 1800 N/cm²

STORAGE CONDITIONS

Minimum 24 months if stored in properly sealed packaging in a dry place at a temperature between +10°C and +20°C. Close packaging well after use. The individual components may not come in contact with each other or with water. Store dry in sealed packaging between +10°C and +20°C.